

PRODUCT AH-4075PMA/XYL

1. GENERAL DESCRIPTION

- A variety of two-component Polyurethane Coating can be as a hardener

2. FEATURES

- Weather resistance
- Flexibility

3. APPLICATIONS

- Automobile repair, Heavy duty protective coating
- Wood, Metal
- Plastic, Synthetic leather
- Adhesives, Film coating

4. SPECIFICATIONS

Property	Unit	Value
Non Volatile Content	-	74.0 - 76.0
Viscosity (25℃)	Gardner	E - H
NCO CONTENT	%	16.2 - 16.8
Free Monomer	%	0.5 Max

5. GUIDELINES for USE

- Be sure to read the MSDS, Technical data and Warnings before using please.
- Likely to result in injury due to solvent vapors compressed, please be careful.
- Has the possibility change the viscosity of the product when stored for a long time.

6. STORAGE GUIDE

- After use, the remaining sealed to prevent moisture from entering the indoor storage, please.

7. REFERENCES

- When used alone may be not cure.
- There is a possibility to be a compatibility problem when you use with another hardener.
- Mixed with the water-soluble resin used is the cause of the defects.

All data, statement, and recommendations made herein are based upon information we to be believe to be reliable, but are made without any representation or guaranty or warranty of accuracy and are made with reservation of all patent right. Also statement regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patents rights or in violation of any application laws or regulations.

Research Center: P.O. Box 305-805 #217-2, Shinseong-dong, Yuseong-gu, Daejeon, Korea
 Tel. 82-42-879-0300 Fax. 82-42-879-0399 Web site: www.akc.co.kr

